

Positiv-Plus

1329

Water-based **positive stain** for softwoods for **industrial use**

PRODUCT DESCRIPTION

General

Water-based positive stain with high light fastness for sanded and brushed softwoods when a positive stain appearance is to be achieved in a single operation. The product can be overcoated with water-based and solvent-based wood coatings.

Special properties and standards



- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

Application area




For furniture, interior fixtures, wall paneling and wood ceilings.

Depending on the furniture coating used, the product is suitable for surfaces of furnitures and interior finishing in application areas II – IV according to ÖNORM A 1610-12.

Application in combination with a suitable topcoat system.

PROCESSING

Processing instructions



- Please stir product well before and during use.
- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- A staining application with Airmix or Airless low pressure device is also possible. An application with brush or sponge is also possible on small dimensioned surfaces.
- Less absorbent wood types require less application compared to more absorbent timber.
- Various types of wood such as larch, Swiss stone pine etc. contain water-soluble substances, which become active when overcoating with water-based furniture coatings. To prevent discolouration or marks when painting wood rich in active substances we therefore recommend priming them first with Aduro Primer (2523).
- The color changes if the liquid stain comes into contact with metal.
- Do not return the product from the application tool or product contaminated with wood dust to the original container.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please observe our **ARL 110 - Working guidelines for staining Wood**.

Application technique



	Cup gun
Spraying nozzle Ø (mm)	1,5
Spraying pressure (bar)	2,0 - 2,5
Yield per application (m ² /l)	6 - 8
Applied quantity per application (g/m ²)	60 - 70

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)



Recoatable (solvent-based coatings)	12 hour(s)
Recoatable (water-based coatings)	5 hour(s)

The positive effect develops during the first stage of drying (approx. 30 minutes), during which no forced drying with circulating air is allowed.

The figures given above are reference values. Drying depends on the substrate, layer thickness, temperature, air exchange, relative humidity, stacking pressure and stacking conditions.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

Cleaning the working equipment



With water immediately after use.

To remove dried paint residues we recommend using Aqua-Cleaner (8029) (diluted 1:1 with water).

SUBSTRATE

Type of substrate

Softwoods

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, etc. and free from dust, as well as tested for suitability for coating.

Substrate preparation

Grit size 120 brushing, chopping, roughing or planing Deresinate softwoods with high resin content such as pine or Swiss pine and sand down with grit size 120.

Rinsing the sanded wood and, once it has dried, sanding it smooth with grit size 120 is beneficial.

Brushed, hewn, rough-planed or planed surfaces are stained without any further pre-treatment.

Please observe our **ARL 021 - Working guideline for deresination**.

COATING SYSTEM

Stain application

1 x Apply evenly and with moderate excess along the direction of the wood fiber so that the surfaces appear slightly wet.

Subsequent coating

2 x coating with ADLER furniture coating, with intermediate sanding
The product can be coated with both water- and solvent-based ADLER furniture coatings. For light stain shades, we generally recommend the use

of lightfast coatings such as
e.g. Aduro Legnopur (2513) or Bluefin Resist (2963).

It is not possible to use Aduro Isoliergrund (2502).

For white stained surfaces we recommend to apply additionally one layer of Legnopur, tinted with 1.0 % up to a max. of 3.0 % Solva-Tint Polarweiß (9035040114). Alternatively, a water-based furniture coating such as Bluefin Top-Antiscratch, tinted with 1.0 to max. 3.0 % Aqua-Tint Polarweiß (9009040114), can be used. Avoid any overlap when spraying!

ORDERING INFORMATION

Size of trading unit

11, 5l

Colour shades / Glosslevels



Positiv-Plus (1329) & colour number

Special colours on request.

If it is thinned excessively, the inherent colour of the wood and the natural yellowing of the wood can lead to noticeable colour changes over a period of time.

Prior to applying the stain and the coating, you should always stain and fix a sample of the original wood and treat it with the intended coating material in order to assess the final colour shade.

Only use stains from the same batch for a commission.

Supplementary products

Aduro Antiscratch (2517)
Aduro Legnopur (2513)
Aduro Primer (2523)
Aqua-Cleaner 8029 (8029)
Aqua-Tint Polarweiß (9009040114)
Bluefin Resist (2963)
Bluefin Top-Antiscratch (2960)
Solva-Tint Polarweiß (9035040114)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 1 year(s) in the original sealed containers.

Cool, but frost-free.

Close opened containers well and use up the content as soon as possible.

Safety information



The product is only suitable for industrial use.

The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2).

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.